

7th Int. Vacuum Insulation Symposium, Sept. 28-29, 2005, Zürich-Dübendorf, Switzerland

Fast Method to Check the Thermal Performance of Metal-Covered VIP

D. Büttner,

C. Stark, M. Keller, J. Fricke

Bavarian Center for Applied Energy Research

Introduction

Measurement Method

Theory

Simulations

Summary and Outlook

Vacuum insulation panel with metal envelope



metal envelope

vacuum panel core

stainless steel

0.8 ... 4 mm

surface: plane

or with lug pattern

Characterisation of thermal performance:

Foil lift-off method to determine the internal pressure is not applicable.

Thermal measurements:


- stationary measurement of thermal conductivity:
very slow, both sides of VIP must be accessible
- transient measurement of **effusivity**:
problem: 2 layers with extreme different properties,
→ special method required

Measurement of Effusivity: Set-up



ZAE BAYERN

Sketch of the measurement set-up



heat capacity per area: C''_E , C''_H for envelope, heater

Effusivity: $b = \sqrt{\lambda \rho c_p}$

Heat flux into a semi-infinite homogeneous region ($x \geq 0$)
for a sudden temperature rise $T_0 \rightarrow T_{ref}$ at time $t = 0$ at surface $x = 0$:

$$\dot{q}(t) = \frac{b \cdot \Delta T_{ref}}{\sqrt{\pi \cdot t}}$$

$$\Delta T_{ref} = T_{ref} - T_0$$

Problem:

2 layers with extremely different thermal properties,
effusivity of layer 2 is to be measured.


The pre-heated sensor is put onto the metal envelope

- Short-term range: accelerated heating-up of metal envelope:
 - Overheating of heater with $T_H(t) = T_{\text{ref},A} > T_{\text{ref}}$ for $0 \leq t \leq t_A$,
 t_A : optimized end of overheating to avoid overshoot of envelope temperature T_E above the long-term reference temperature T_{ref} ;
 - Intercooling: heater cools down from $T_{\text{ref},A} \rightarrow T_{\text{ref}}$,
envelope temperature still rises towards T_{ref} .
 - When $T_H(t) \approx T_{\text{ref}}$: controlled heating to keep $T_H(t) = T_{\text{ref}} = \text{constant}$.
- Long-term range: effusivity measurement on VIP core.

Accelerated Heating-up of Metal Envelope (Theory)

$d_E = 4 \text{ mm}$

$\alpha = 200 \text{ W}/(\text{m}^2 \cdot \text{K})$



Accelerated Heating-up: Overheating (ideal case)

Overheating of heater with $T_H = T_{ref,A} > T_{ref}$ at $0 \leq t \leq t_A$

$$\Delta T_{E,A}(t) = \Delta T_{ref,A} \cdot \left[1 - \exp\left(-\frac{t}{\tau_E}\right) \right]$$

$$\dot{q}_{E,A}(t) = \alpha \cdot \Delta T_{ref,A} \cdot \exp\left(-\frac{t}{\tau_E}\right) = \dot{q}_{E,A,0} \cdot \exp\left(-\frac{t}{\tau_E}\right)$$

with the characteristic time

$$\tau_E = \frac{C_E''}{\alpha} = \frac{\rho_E \cdot c_E \cdot d_E}{\alpha}$$

and the initial heat flux

$$\dot{q}_{E,A,0} = \alpha \cdot \Delta T_{ref,A} = C_E'' \cdot \Delta T_{ref,A} / \tau_E$$

Intercooling until $T_H = T_{ref}$ at $t_A \leq t \leq t_B$.

$$T_H(t) = T_{ref} + [T_{ref,A} - T_{ref}] \cdot \exp\left(-\frac{t - t_A}{\tau_{E,H}}\right)$$

$$T_E(t) = T_{ref} + [T_{E,A} - T_{ref}] \cdot \exp\left(-\frac{t - t_A}{\tau_{E,H}}\right)$$

$$\dot{q}(t) = \alpha \cdot (T_H - T_E) = \alpha \cdot [T_{ref,A} - T_{E,A}] \cdot \exp\left(-\frac{t - t_A}{\tau_{E,H}}\right)$$

with the characteristic time $\tau_{E,H}$:

$$\frac{1}{\tau_{E,H}} = \frac{\alpha}{C_H''} + \frac{\alpha}{C_E''} = \frac{1}{\tau_H} + \frac{1}{\tau_E}$$

Characteristic times:

VIP envelope made of stainless steel with $\rho_E \cdot c_E = 4 \cdot 10^6 \text{ W} \cdot \text{s}/(\text{m}^3 \cdot \text{K})$,
and a heater with $C''_H = 9 \cdot 10^3 \text{ W} \cdot \text{s}/(\text{m}^2 \cdot \text{K})$:

α	$[\text{W}/(\text{m}^2 \cdot \text{K})]$	1000	200	200
d_E	$[\text{mm}]$	1	1	4
C''_E	$[\text{W} \cdot \text{s}/(\text{m}^2 \cdot \text{K})]$	$4 \cdot 10^3$	$4 \cdot 10^3$	$16 \cdot 10^3$
τ_E	$[\text{s}]$	4	20	80
$\tau_{E,H}$	$[\text{s}]$	2.8	13	29

The long-term range is described by the

modified equation: $\dot{q}(t) = \frac{b \cdot \Delta T_{ref}}{\sqrt{\pi \cdot (t - t_0)}}$

with the unknown **effective starting time t_0**
due to non-idealised starting conditions.

Evaluation:

$$\frac{1}{\dot{q}^2} = \frac{\pi}{b^2 \cdot (\Delta T_{ref})^2} \cdot (t - t_0) = \frac{\pi}{\lambda \cdot \rho \cdot c \cdot (\Delta T_{ref})^2} \cdot (t - t_0) = A \cdot t + B$$

For optimization of measurement design and procedure:

Numerical simulations with variation of parameters

d_E , α , λ_{VIP} , guard ring width

Example:

Metal-covered VIP with


$$d_E = 1 \text{ mm} ,$$

$$\alpha = 200 \text{ W}/(\text{m}^2 \cdot \text{K}) ,$$

$$\lambda = 16 \cdot 10^{-3} \text{ W}/(\text{m} \cdot \text{K})$$


Simulations: Accelerated Heating-up

$$d_E = 1 \text{ mm} , \alpha = 200 \text{ W}/(\text{m}^2 \cdot \text{K}) , \lambda = 16 \cdot 10^{-3} \text{ W}/(\text{m} \cdot \text{K})$$



Simulations: Long-term Range


$d_E = 1 \text{ mm}$, $\alpha = 200 \text{ W}/(\text{m}^2 \cdot \text{K})$, $\lambda = 16 \cdot 10^{-3} \text{ W}/(\text{m} \cdot \text{K})$



Simulations: Evaluation of $1/q^2$ - Linear Fit

$$\frac{1}{\dot{q}^2} = \frac{\pi}{\lambda \cdot \rho \cdot c \cdot (\Delta T_{ref})^2} \cdot (t - t_0) = A \cdot t + B$$


$d_E = 1 \text{ mm}$, $\alpha = 200 \text{ W}/(\text{m}^2 \cdot \text{K})$, $\lambda = 16 \cdot 10^{-3} \text{ W}/(\text{m} \cdot \text{K})$



Simulations: Evaluation of $1/q^2$ - Linear Fit

$$\frac{1}{\dot{q}^2} = \frac{\pi}{\lambda \cdot \rho \cdot c \cdot (\Delta T_{ref})^2} \cdot (t - t_0) = A \cdot t + B$$

$d_E = 1 \text{ mm}$, $\alpha = 200 \text{ W}/(\text{m}^2 \cdot \text{K})$



Results from simulations

- long-term range:
evaluation procedure for effusivity b or conductivity λ is applicable
- initial (accelerated) heating-up:
an estimate for the contact resistance can be derived (not shown)
- required width of guard ring (not shown)

Fast method to check the thermal performance of metal-covered VIP

- theoretical description
- numerical simulations

Currently first tests with a prototype are under way.

Construction and control of an optimized sensor is required.

Further possible applications:

The presented method is not only applicable for metal-covered VIPs, but might also be used for build-in VIPs or for VIPs which are enclosed in a protection layer.

Acknowledgment:

These investigations are performed within the project

„Energieoptimiertes Bauen, Teilkonzept 1: Aufbau einer Koordinationsstelle für die nationalen Tätigkeiten zum ECBCS-Annex 39 „High Performance Thermal Insulations for Buildings“ (HiPTI) der Internationalen Energieagentur (IEA) und Qualitätskontrolle von Vakuumisulationspaneelen [0327321E]“

**which is funded by the BMWA
(German Federal Ministry of Economics and Labour).**